

WOODPECKER

NATURALLY INSPIRED FLOORING

TECHNICAL DATA SHEET CHEPSTOW DISTRESSED CHARCOAL OAK

PRODUCT DETAILS

PRODUCT CODE	65-AOC-001
CONSTRUCTION	Engineered Wood
SPECIES	Oak
WEAR LAYER	6mm
BACKING	Eucalyptus Ply
THICKNESS	21mm
WIDTH	190mm
LENGTH	1900mm
	<i>Packs include cut lengths</i>
PACK SIZE	1.444m ²
PLANKS PER PACK	4
GRADE	Rustic
FINISH	Hardwax Oil
JOINT TYPE	Tongue & Groove
BEVELLED EDGES	All 4 Edges
FIXING METHOD	Float, nailed or stuck down
UNDERFLOOR HEATING	Suitable if stuck down
TOG RATING	1.2



TECHNICAL CRITERIA

ORIGIN	Europe
RESPONSIBLE CERTIFICATION	FSC
JANKA HARDNESS RATING	1,360 lbf (6,000N)
FORMALDEHYDE EMISSION	E1
PENTACHLOROPHENOL EMISSION	Undetected
REACTION TO FIRE	Dfl s1
THERMAL CONDUCTIVITY	0.16 W / mK

GRADING CRITERIA

MAXIMUM SIZE OF SOUND KNOTS	50mm
MAXIMUM SIZE OF DEAD KNOTS	30mm
HEARTWOOD	Allowed
SAPWOOD	Allowed
INSECT HOLES	Not Allowed
FILLER	Allowed
COLOUR VARIATION	Allowed
SMALL CRACKS	Allowed
ROT	Not Allowed

SPECIFICATION DISCLAIMER

This technical data sheet was written by Woodpecker Flooring and at the time of writing and publication, all information was specified correctly. The company reserves the right to change specification without notice. Customers should confirm that the floor of their choice is still available with the specification shown.

Woodpecker House, 26 Pant Glas Industrial Estate, Bedwas, Caerphilly CF83 8DR

T: 02920 888 223 F: 02920 881 694 info@woodpeckerflooring.co.uk

WWW.WOODPECKERFLOORING.CO.UK



WOODPECKER

NATURALLY INSPIRED FLOORING

TECHNICAL DATA SHEET CHEPSTOW DISTRESSED CHARCOAL

PRODUCT DETAILS

PRODUCT CODE	65-AOC-002
CONSTRUCTION	Engineered Wood
SPECIES	Oak
WEAR LAYER	6mm
BACKING	Eucalyptus Ply
THICKNESS	21mm
WIDTH	240mm
LENGTH	2200mm
	<i>Packs include cut lengths</i>
PACK SIZE	2.11m ²
PLANKS PER PACK	4
GRADE	Rustic
FINISH	Hardwax Oil
JOINT TYPE	Tongue & Groove
BEVELLED EDGES	All 4 Edges
FIXING METHOD	Float, nailed or stuck down
UNDERFLOOR HEATING	Suitable if stuck down
TOG RATING	1.2



TECHNICAL CRITERIA

ORIGIN	Europe
RESPONSIBLE CERTIFICATION	FSC
JANKA HARDNESS RATING	1,360 lbf (6,000N)
FORMALDEHYDE EMISSION	E1
PENTACHLOROPHENOL EMISSION	Undetected
REACTION TO FIRE	Dfl s1
THERMAL CONDUCTIVITY	0.16 W / mK

GRADING CRITERIA

MAXIMUM SIZE OF SOUND KNOTS	50mm
MAXIMUM SIZE OF DEAD KNOTS	30mm
HEARTWOOD	Allowed
SAPWOOD	Allowed
INSECT HOLES	Not Allowed
FILLER	Allowed
COLOUR VARIATION	Allowed
SMALL CRACKS	Allowed
ROT	Not Allowed

SPECIFICATION DISCLAIMER

This technical data sheet was written by Woodpecker Flooring and at the time of writing and publication, all information was specified correctly. The company reserves the right to change specification without notice. Customers should confirm that the floor of their choice is still available with the specification shown.

Woodpecker House, 26 Pant Glas Industrial Estate, Bedwas, Caerphilly CF83 8DR

T: 02920 888 223 F: 02920 881 694 info@woodpeckerflooring.co.uk

WWW.WOODPECKERFLOORING.CO.UK

