

WOODPECKER

NATURALLY INSPIRED FLOORING

TECHNICAL DATA & APPLICATION

MS PARQUET ADHESIVE

Woodpecker MS Parquet is a single component, moisture curing, polyurethane, flexible parquet adhesive. It is suitable for porous and non-porous surfaces such as sand-cement, concrete and wood. It contains no water or solvents, reducing the risk of distortion through moisture to the wood floor. It is non-flammable and quick setting to develop a high bond strength. It is protected against bio-degradation and suitable for use over underfloor heating.



TECHNICAL DATA

MATERIAL.....	Polyurethane
CURING SYSTEM.....	Moisture Curing
CONSISTENCY.....	Paste
COLOUR.....	Pale Brown
OPEN TIME AT 70° AND 50% RH.....	Approx 30mins

INSTALLATION DATA

(based on optimum conditions of 70°F air temperature and 50% RH air humidity)

- Underfloor heating must be switched off for a minimum of 48 hours before use.
- Acclimatise cold adhesive to room temperature before use.
- Working open time approx. 30 minutes.
- Wait 24 hours before allowing foot traffic.

CONSUMPTION:

125-150 SF/container depending on the notched trowel used. We recommend a 1/8" - 1/4" notch depending on the condition of the subfloor.

SUBFLOOR:

The subfloor must be even, dry (<65% RH), clean, smooth, sound and free from cracks. Residues such as old adhesive, oil and stains may act negatively on the adhesion strength. Uneven surfaces must be levelled to within 3mm over any 2m area. Smooth surfaces like anhydrite should be roughened and any surface laitance removed. A preliminary compatibility test is recommended on every surface.

APPLICATION:

Apply the adhesive to the prepared surface using a suitable notched trowel. Do not apply more than can be covered by the flooring within 30 minutes. Lay the planks and ensure good adhesive transfer (minimum 80% cover). Loading the planks with weights will improve the transfer. Allow a minimum 1/2" expansion gap between the planks and walls. Do not apply the adhesive at temperatures below 60° or above 80° and at a relative humidity above 75%. Do not dilute the adhesive. To remove fresh adhesive, apply acetone. Apply the adhesive to the prepared surface using a notched trowel.

STORAGE:

Shelf-life is 9 months in original, closed packaging.

SPECIFICATION DISCLAIMER

This technical data sheet was written by Woodpecker Flooring and at the time of writing and publication, all information was specified correctly. The company reserves the right to change specification without notice. Customers should confirm that the product is still available with the specification shown.

Woodpecker House, 29 Pant Glas Industrial Estate, Bedwas, Caerphilly CF83 8DR

T: 02920 888 223 F: 02920 881 694 info@woodpeckerflooring.co.uk

WWW.WOODPECKERFLOORING.CO.UK